

# 2K HS Extra Clear RTS

# LESONAL

Technical Data Sheet

08 / 06 / 2017

L1.05.06 UK & Ireland


Clearcoats

## Description


Two component, isocyanate hardening, quick drying clearcoat in aerosol.

To be used for spot repairs up to panel repairs. The product is activated by pushing the red button on the pin at the bottom.


### Preparation



Shake well



Place button on pin at bottom




Push button once to activate


### Application



Shake at least 2 min. before use




Distance 20-30 cm




Apply in 2 single coats

### Flash-off




5 - 10 minutes at 20°C

### After use



Invert aerosol to clear nozzle

### Drying



20°C

60°C

7 hours

30 minutes

### Protection



Read complete technical data sheet for detailed product information

# 2K HS Extra Clear RTS

# LESONAL

Technical Data Sheet

08 / 06 / 2017

L1.05.06 UK & Ireland

Clearcoats

## Description

Two component, isocyanate hardening, quick drying clearcoat in aerosol.  
To be used for spot repairs up to panel repairs. The product is activated by pushing the red button on the pin at the bottom.

## Product and additives

Lesonal 2K HS Extra Clear RTS

## Chemical Basis

2K HS Extra Clear - acrylic resins  
Hardener (integrated in canister) - poly isocyanates

## Product activation

Activate product by pushing the red button on the pin at the bottom of the aerosol. Shake for at least 2 minutes before use. After use, invert aerosol to clear nozzle.

## Substrates

Lesonal Basecoat WB  
Lesonal Basecoat WB GT

## Application



Apply two single coats. Allow a flash off time of 5 to 10 minutes.  
For larger areas it is advised to apply 2K HS Extra Clear by conventional spray gun.

## Pot life

After mixing, use within 8 hours at 20° C  
(Potlife can be extended by storage in a cool environment)

## Drying Times



	at 20° C	at 60° C
Dust free	20 min.	5 min.
Tack free	3 hrs	20 min.
Dry to handle	7 hrs	30 min.

## Layer Thickness

25 – 30 micron per coat

# 2K HS Extra Clear RTS

**LESONAL**

Technical Data Sheet

08 / 06 / 2017

L1.05.06 UK &amp; Ireland

Clearcoats

**Shelf life**

1 year

**VOC**

The EU limit value for this product (product category: IIB.e) in ready to use form is max. 840 g/litre VOC.  
The VOC content of this product in ready to use form is max. 623 g/litre.

**Caution**

This product contains isocyanates. Wear suitable personal protective equipment and use only in an environment designed for the application of isocyanate containing products.

**Akzo Nobel Coatings LTD**

**Address:** Unit 2B, Didcot Park  
Churchward, Southmead Industrial Estate  
Didcot, Oxfordshire, OX11 7HB  
**Tel:** 00 44 (0)1235 862226

**FOR PROFESSIONAL USE ONLY**

**IMPORTANT NOTE** The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws; any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfill the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advices given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.

Brand names mentioned in this data sheet are trademarks of or are licensed to AkzoNobel.

**Head Office**

Akzo Nobel Car Refinishes B.V., PO Box 3 2170 BA Sassenheim, The Netherlands. [www.Lesonal.com](http://www.Lesonal.com)

